



# PRODUCT TECHNICAL DATA SHEET

## BP-1 Primer/Adhesive

Main Description --- The BP-1 Primer/Adhesive system is a polyurethane based system designed for high performance applications. This primer promotes bonding between Aquawrap® and the substrate and adds to the corrosion barrier provided by the composite layup. BP-1 contains glass fibers for additional strength. It works well with steel, stainless steel, aluminum, copper, wood, and concrete. It may also be used on some plastics such as PVC, polyethylene, and fiberglass. This system is intended for use on dry substrates and will not work properly in wet surfaces. This system is composed of two components that require mixing prior to use. Color is light yellow.

ATTENTION: All of the following data are based on laboratory conditions, at room temperature. Field conditions can radically change the characteristics of this product. Field testing is strongly recommended prior to application. Temperature can have a severe impact on cure times. Allow adequate time for application.

### BP-1 System

Physical Properties			
<b>Working (pot) Life:</b>	45 min. at 25°C (77°F)	<b>Mix Ratio:</b>	Factory Ratioed
<b>Application Temps:</b>	0-99°C (33-211°F)	<b>Service Temps:</b>	-40-121°C (-40 - 250°F)
<b>Cure Time (dry to touch):</b>	60-90 min. at 25°C (77°F)	<b>Full Cure:</b>	2 days at 25°C (77°F)
<b>Usual Packaging:</b>	Factory Ratioed	<b>Shelf Life:</b>	1 year in sealed container
<b>Bond Strength:</b>	Concrete – 225 psi	Metals 1000 psi	Wood – 500 psi Plastic – 350 psi

**Surface Preparation**  
 Surface to be coated must be clean and free of oils, grease, and loose contamination. Any filler material used to contour surface anomalies must be sanded and abraded to provide good adhesion.

**Application**  
 Individually mix the BP-1 components thoroughly by hand. Normal mixing procedure is to pour the contents of Part B into the Part A container and blend. Pot life from this point is approximately 45 minutes at 77° F. Do not leave mixed contents in a closed container. Apply immediately using a brush or roller.  
 Refer to BP-1 Installation Instructions for details.

**Transport**  
 BP-1 Primer/Adhesive is non-regulated by the USDOT, IATA and IMO and may ship non-hazardous.

Storage & Handling – Store at 50-80° F in a dry place. Leftover materials cannot be reused. Dispose of remnants properly. Always use clean, dry tools when mixing or applying the matrix. Mix ratios are generally pre-determined and packaged accordingly. Normal mixing procedure is to pour the contents of the Part B container into the Part A container and mix thoroughly. Use immediately.

CAUTION: Some persons may be irritated by these compounds. Use caution and PPE. See MSDS.  
 FOR INDUSTRIAL USE BY PROFESSIONALLY TRAINED PERSONNEL ONLY.

**ABSTRACT OF WARRANTY:** There is no warranty, express or implied, with respect to this product or any of its properties or applications. All of the data printed on this Technical Data Sheet is approximate and may not apply to your situation. Air Logistics liability with respect to the use and or application of this product is strictly limited to the replacement costs of any product shown to be defective by laboratory testing. See our full Terms and Conditions for the actual warranty and terms of sale.  
**ATTENTION:** No representation is made as to the accuracy or correctness of the information contained herein, other than to state that it is presented by this organization in good faith and we believe it to be correct and accurate per the limits of our understanding and training as of the date of first publication. The user or handler of this product is warned to take the most conservative and safest interpretation possible of all information contained herein and to use the most extreme personal protection measures and exposure limitations prudently dictated by the specific usage or handling situation, this product’s MSDS information and good industrial safety and hygiene practices.  
 (Kevlar® is a registered trademark of E.I. Dupont Corporation)